


VT-4B7 SP

Aluminum Base Laminate

UL Approval: E214381 Version: B2



CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.
308 TaiShan Rd,
New District Suzhou,
Jiangsu, P.R. China 215129
T: +86 512-68091810
Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe
Unit 1 Trojan Business Centre,
Tachbrook Park Estate,
Leamington-Spa, CV34 6RH, UK
T: +44 1926-889822
Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA
700 Lee St., Elk Grove Village,
Illinois, IL 60007,
United States of America
T: +1 630-4221627
Email: saleseast@ventec-usa.com

www.ventecclaminates.com

VT-4B7 SP

UL Approval: E214381 Version: B2

Aluminum Base Laminate

General Information

- > Thermal conductivity -- 7.0 W/mK
- > Ceramic Filled
- > Halogen Free
- > Flammability UL94 V-0
- > MOT 130°C
- > Selective Preference Dielectric for Ultra Low Thermal Resistance

Application

- > Matrix LED for Auto Bulb
- > High Power LED for Projector
- > Electric Power Steering



Storage Condition & Shelf Life

		Laminate
Storage Condition	Temperature	Room
	Relative humidity	/
Shelf Life		24 months

The RCF exceeding shelf life should be retested.

Designation of IMS Laminate

VT-4B7 SP 1.0mm Alu (5052) 1oz Cu



CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.
308 TaiShan Rd,
New District Suzhou,
Jiangsu, P.R. China 215129
T: +86 512-68091810
Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe
Unit 1 Trojan Business Centre,
Tachbrook Park Estate,
Leamington-Spa, CV34 6RH, UK
T: +44 1926-889822
Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA
700 Lee St., Elk Grove Village,
Illinois, IL 60007,
United States of America
T: +1 630-4221627
Email: saleseast@ventec-usa.com

www.ventec laminates.com

VT-4B7 SP

Aluminum Base Laminate

UL Approval: E214381 Version: B2

Laminate Properties

Item		Test Method (IPC-TM-650)	Unit	VT-4B7 SP
Thermal Conductivity		ISO22007-2	W/m*K	7.0
Thermal Impedance		ISO22007-2	°C*in ² /W	0.009
Tg	DSC	2.4.25	°C	100
Td	TGA	ASTM D3850	°C	380
Thermal Stress	Solder Dip @ 288°C	2.4.13.1	Minute	≥5
Hi-Pot Withstand	DC	2.5.7.2	V	1000
Breakdown Voltage	AC	2.5.6.3	V	3000
Dk @ 1MHz	C-24 /23 / 50	2.5.5.3	—	4.8
Df @ 1MHz	C-24/ 23 / 50	2.5.5.3	—	0.016
Volume Resistance	After Moisture	2.5.17.1	MΩ-cm	5.0E+8
	E-24/125			3.0E+7
Surface Resistance	After Moisture	2.5.17.1	MΩ	2.0E+7
	E-24/125			5.0E+6
Peel strength (1oz)	As Received	2.4.8	Lb/in	4.5
CTI	As Received	ASTM D3638	V	600
Flammability	As Received	UL 94	Rating	V-0
RTI	Electric	UL 94	°C	130
	Mechanical	UL 94	°C	130

All test data provided are typical values and not intended to be specification values.

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.

308 TaiShan Rd,
New District Suzhou,
Jiangsu, P.R. China 215129

T: +86 512-68091810

Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe

Unit 1 Trojan Business Centre,
Tachbrook Park Estate,
Leamington-Spa, CV34 6RH, UK

T: +44 1926-889822

Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA

700 Lee St., Elk Grove Village,
Illinois, IL 60007,
United States of America

T: +1 630-4221627

Email: saleseast@ventec-usa.com

www.ventec laminates.com

VT-4B7 SP

Aluminum Base Laminate

UL Approval: E214381 Version: B2

Availability

Laminate

Item		Availability
Standard Size	Imperial	18.11*24.02, 20.08*24.02, 20.98*24.02, 18.11*48.03, 20.02*48.03, 20.98*48.03
	Metric	460*610, 510*610, 533*610, 460*1220, 510*1220, 533*1220
Copper Weight		1/3oz, Hoz, 1oz, 2oz, 3oz, 4oz, 6oz
Aluminum Thickness		0.6mm, 0.8mm, 1.0mm, 1.2mm, 1.5mm, 2.0mm, 3.0mm
Aluminum Alloy		1100, 5052, or as required

Protective Film for Aluminium Plate

Type	Material	Max Operation Temperature
Standard	PET	170 °C
High Temperature	Polyimide	270 °C

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.
308 TaiShan Rd,
New District Suzhou,
Jiangsu, P.R. China 215129
T: +86 512-68091810
Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe
Unit 1 Trojan Business Centre,
Tachbrook Park Estate,
Leamington-Spa, CV34 6RH, UK
T: +44 1926-889822
Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA
700 Lee St., Elk Grove Village,
Illinois, IL 60007,
United States of America
T: +1 630-4221627
Email: saleseast@ventec-usa.com

www.ventec laminates.com